


**AMENDMENTS TO THE CLAIMS:**

Kindly replace the previous claim set with the claim set which appears below:

1. (previously presented) A mold release composition having a pH of 7 to 11 comprising a functional siloxane, having the following structure:



where R<sub>1</sub>, R<sub>2</sub>, R<sub>3</sub>, R<sub>4</sub>, R<sub>5</sub> and R<sub>6</sub> individually can be the same or different, each being selected from the group consisting of C<sub>1-3</sub> alkyl, vinyl, hydride, and alkoxy groups, where n is about 0 to about 100,000, and where P<sub>1</sub> and P<sub>2</sub> can be the same or different, each being selected from the group consisting of silanol, hydride, hydroxyl, alkyl, vinyl, carbinol and carboxy groups;  
a crosslinker, a thickening agent, a base, and water.

Claims 2-5. (cancelled)

6. (previously presented) A mold release composition according to claim 1, wherein the crosslinker has the general formula X-SiABC where X is selected from the group consisting of methyl, vinyl, alkoxy, acetoxy, hydride and ethyl groups, and A, B and C are each individually an alkoxy group.

Claims 7-8. (cancelled)

9. (previously presented) A mold release composition according to claim 1, having less than 5 grams VOCs per liter of said mold release composition.

Claims 10-11. (cancelled)

12. (previously presented) A mold release composition according to claim 1, further comprising at least one component selected from the group consisting of a wetting agent, a surfactant, a catalyst, a slip agent, a dye and a transfer control agent.

Claims 13-20. (cancelled)

21. (previously presented) A mold release composition according to claim 1, having a viscosity of 10-10,000 cP at 25°C.

22. (cancelled)

23. (previously presented) A mold release composition according to claim 1, said functional siloxane having the following structure:  $\text{HO}(\text{CH}_3)_2\text{-Si}(\text{O-Si}(\text{CH}_3)_2\text{-O-Si}(\text{CH}_3)_2)_x\text{-O-Si}(\text{CH}_3)_2\text{OH}$ , where x is selected such that said functional siloxane has a molecular weight in the range of 4,000 - 100,000.

Claims 24-37. (cancelled)

38. (previously presented) A mold release composition according to claim 1, said mold release composition being curable at room-temperature.

39. (currently amended) A mold release composition according to claim 1, comprising the following composition:

- 0.04-2.99 weight percent silanol-functional siloxane;
- 0.018-4.98 weight percent alkoxy-functional crosslinker;
- 0.009-2 weight percent catalyst;

0.04-4.8 weight percent thickening agent activatable at a pH of 7 to 11;  
and  
0.1-2 weight percent base.

40. (previously presented) A mold release composition according to claim 1, wherein at least one of  $P_1$  and  $P_2$  is hydroxyl.

41. (previously presented) A mold release composition according to claim 1 wherein the crosslinker is selected from a tri-alkoxy functional silane and a tetra-alkoxy functional silane.

42. (previously presented) A mold release composition according to claim 1, having a shelf life of greater than five months at about 25°C.

43. (previously presented) A mold release composition according to claim 1, wherein the thickening agent is activatable at a pH of 7 to 11, the activated thickening agent providing the mold release composition with a viscosity of 10-10,000 cP at 25°C.

44. - 51. cancelled


52. (new) The mold release composition according to claim 1 wherein the base is a separate component from the functional siloxane, the crosslinker and the thickening agent.

53. (new) The mold release composition according to claim 1 wherein the base is an aliphatic ethanolamine additional to the functional siloxane, the crosslinker and the thickening agent.

54. (new) The mold release composition according to claim 1 wherein the mold release composition has no more than 1 percent by weight of composition of non-functional siloxane.

55. (new) The mold release composition according to claim 1 wherein cured products of the mold release composition have substantially no detrimental transfer to the surface of a composite molded part.

56. (new) A mold release composition prepared from a mixture comprising:  
0.04 to 3 percent by weight of mixture of a functional siloxane, having the following structure,



where  $\text{R}_1$ ,  $\text{R}_2$ ,  $\text{R}_3$ ,  $\text{R}_4$ ,  $\text{R}_5$  and  $\text{R}_6$  individually can be the same or different, each being selected from the group consisting of  $\text{C}_{1-3}$  alkyl, vinyl, hydride, and alkoxy groups, where  $n$  is about 0 to about 100,000, and where  $\text{P}_1$  and  $\text{P}_2$  can be the same or different, each being selected from the group consisting of silanol, hydride, hydroxyl, alkyl, vinyl, carbinol and carboxy groups;

0.18 to 5 percent by weight of mixture of a functional crosslinker having the formula  $\text{X-SiABC}$  where  $\text{X}$  is selected from the group consisting of methyl, vinyl, alkoxy, acetoxy, hydride and ethyl groups, and  $\text{A}$ ,  $\text{B}$  and  $\text{C}$  are each individually an alkoxy group;

0.04 to 5 percent by weight of mixture of a thickening agent activatable at a pH of 7 to 11, the activated thickening agent providing the mold release composition with a viscosity of 10-10,000 cP at  $25^\circ\text{C}$ ;

0.1 to 2 percent by weight of mixture of an ethanolamine base additional to the functional siloxane, the crosslinker and the thickening agent;


optionally, 0.05 to 38 percent by weight of mixture of at least one component selected from the group consisting of catalyst, wetting agent, surfactant, slip agent, dye and transfer control agent; and

water;

wherein the mold release composition has no more than 1 percent by weight of mixture of non-functional siloxanes, a pH of 7 to 11 and a shelf life of greater than five months at about 25°C.

57. (new) A mold release composition prepared from a mixture consisting essentially of:

a functional siloxane, having the following structure,



where  $\text{R}_1$ ,  $\text{R}_2$ ,  $\text{R}_3$ ,  $\text{R}_4$ ,  $\text{R}_5$  and  $\text{R}_6$  individually can be the same or different, each being selected from the group consisting of  $\text{C}_{1-3}$  alkyl, vinyl, hydride, and alkoxy groups, where  $n$  is about 0 to about 100,000, and where  $\text{P}_1$  and  $\text{P}_2$  can be the same or different, each being selected from the group consisting of silanol, hydride, hydroxyl, alkyl, vinyl, carbinol and carboxy groups;

a functional crosslinker having the formula  $\text{X-SiABC}$  where  $\text{X}$  is selected from the group consisting of methyl, vinyl, alkoxy, acetoxy, hydride and ethyl groups, and  $\text{A}$ ,  $\text{B}$  and  $\text{C}$  are each individually an alkoxy group;

a thickening agent activatable at a pH of 7 to 11, the activated thickening agent providing the mold release composition with a viscosity of 10-10,000 cP at 25°C;

an ethanolamine base additional to the functional siloxane, the crosslinker and the thickening agent;

water; and

optionally at least one component selected from the group consisting of catalyst, wetting agent, surfactant, slip agent, dye and transfer control agent;

wherein the mold release composition has no more than 1 percent by weight of mixture of non-functional siloxanes, a pH of 7 to 11 and a shelf life of greater than five months at about 25°C.

58. (new) A mold release composition according to claim 57, wherein the mixture is:

0.04-2.99 weight percent functional siloxane;

0.018-4.98 weight percent functional crosslinker;

0.009-2 weight percent catalyst;

0.04-4.8 weight percent thickening agent;

0.1-2 weight percent base;

optionally 0.04-36.4 weight percent of the at least one component; and

water.

59. (new) A mold release composition according to claim 57, wherein the mixture consists of the functional siloxane; the functional crosslinker; the thickening agent; the base; the water and optionally the at least one component.